

Trespa International B.V.

P.O. Box 110, 6000 AC Weert Wetering 20, 6002 SM Weert, The Netherlands Tel.: 31 (0) 495 458 358, Fax: 31 (0) 495 458 570 www.trespa.com

CLEANING TRESPA ATHLON

Trespa Athlon panels are specifically designed for interior applications. Their integrated decorative surface is designed for intensive use. It is impact, scratch and wear resistant. Panels are easy to keep clean and as they do not absorb or retain moisture they can be cleaned frequently, using standard cleaning agents and certain disinfectants.

General

The surfaces of Trespa Athlon can be easily cleaned with a dry or damp cloth and, if necessary, a mild household cleaner. Wipe damp surfaces with an absorbent cloth. Use of concentrated acid, caustic or abrasive cleaning agents is not recommended.

Remove severe soiling

Severely dirty surfaces or areas where normal soiling* has built up over a long period of time are easy to clean with hot water and an interior detergent- or soap-based cleaning agent, applied with a sponge or soft nylon brush. Apply the diluted cleaning agent to the surface and leave it to soak. Then rinse off with clean water and dry with an absorbent cloth.

* dust, pencil, ball pen, ink, coffee, tea, fruit juice, lipstick, grease, nicotine stains, shoe polish, urine, soap residues, limescale, water-soluble paints and adhesives.

Occasionally, it may be necessary to remove old stains or very stubborn marks with a liquid cleaner containing very fine polishing particles (attention: the surface may be damaged that way) or with bleach. Wash the surface down thoroughly afterwards with clean water and dry with an absorbent cloth.

Removing special staining

- Solvent-based varnishes and adhesives (nail varnish, rubber stamp ink, aerosol paint), tar and
 other soluble but strong stains should be removed with organic solvents such as acetone, white
 spirit, turpentine or petroleum.
- Remove wax from candles or crayons immediately with water and a mild household cleaning agent. Dried wax stains may first have to be scraped off with a wooden or plastic spatula and the remainder removed with an organic solvent.
- Two part paint or adhesive, synthetic resin and the like should be removed immediately with water or an organic solvent. Once these products have set, they cannot be removed without damaging the surface.
- Rub silicone off dry or use a silicone remover.
- Limescale can be removed with acidic cleaning agents containing approximately 10 % acetic acid or citric acid. The manufacturer's instructions must be strictly followed. Rinse surfaces and edges very thoroughly!

Frequent cleaning

The recommended method for everyday cleaning of Trespa Athlon wall cladding and partitions in shower and changing cubicles or sanitary units is warm water with a mild universal cleaning agent applied with a sponge or soft nylon brush. This is the ideal way to remove most light, recent soiling. Wipe damp surfaces with an absorbent cloth. Use of concentrated acid, caustic or abrasive cleaning agents is not recommended.



Using desinfectants

Both the decorative surface and core of Trespa Athlon are highly resistant to most commonly-used disinfectants such as:

- alcohol, preferably 60-70 % solution in water.
- aldehydes, although not in, or in combination with, quaternary ammonia compounds.
- chlorine separating compounds. However, long term use of these products can cause certain pigments to fade.
- phenols, not to be used for kitchen disinfection.
- peroxide compounds (hydrogen peroxide and organic peracids).
- quartenair ammonia compounds.

Some manufacturers offer products containing both cleaning and disinfecting components. These are known as detergent sanitisers, and are intended for simultaneous cleaning and disinfection of light to medium soiled surfaces in rooms where there is no great risk of infection.

Caution

Always follow the manufacturer's instructions carefully when using any cleaning agent or disinfectant.

Using a combination of products may cause unwanted chemical reactions which produce harmful gases.

When surfaces have been cleaned with aggressive cleaning agents, they should be rinsed well to dilute the cleaning agent and prevent it from drying on the panel surface.

Document created by: Trespa Technology Center / Product Management - Code: U5206 - Version: March 2010

Responsibility

Despite the utmost care and attention to the content of this document by Trespa International B.V., it cannot give any warranty as to the accuracy or completeness of the information in this document. The information in this document is intended to serve general information purposes only. Trespa International B.V. makes no warranties or representations, express or implied that the information in this document is fit for the purpose of the reader. Trespa International B.V. does not accept any liability for any direct or indirect damages of whatever nature, in anyway resulting from the use of this document and/or the use of information that is gathered through this document.

© All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or made public, in any form or by any means, either graphic, electronic or mechanical, including photocopying, recording or otherwise, without the prior written permission of Trespa International B.V.

Registered trademarks

® Trespa, Meteon, Athlon, TopLab, TopLab PLUS, TopLab ECO-FIBRE, Virtuon, Volkern, Mystic Metallics and Trespa Essentials are registered trademarks of Trespa International B.V.